

Marine Paint Manual

Reference No. : 08 - 02

Issue Date: June 2013 (ES)

NIPPON E-MARINE PRIMER

A two-pack pure epoxy resin based anticorrosive paint which provides excellent resistance to water and chemicals. Up to 150 µm can be applied with a single coat. There is no maximum limit in the interval of by-self overcoating.

Suitable Use	Anticorrosive primer for boottop, topsides, decks, holds, superstructure, etc.		
Type	Pure epoxy (Two-pack)		
Color	Red, Gray		
Gloss	Flat		
Volume Solids	60 ± 2% (ISO3233:1998)		
Typical Dry Film Thickness	75 ~ 150 µm		
Approx. Wet Film Thickness	125 ~ 250 µm		
Theoretical Coverage	6.00 m ² / L (100 µm)		
Drying Time	Surface Dry	2 hours (5)	1 hour (20) 40 minutes (30)
	Dry Hard	16 hours (5)	7 hours (20) 4 hours (30)
	Full Cure	10 days (5)	5 days (20) 4 days (30)
Interval before Overcoating (by self)	Min.	18 hours (5)	10 hours (20) 7 hours (30)
	Max.	— (5)	— (20) — (30)
Thinner	NIPPON MARINE THINNER 600 (0 ~ 10%, by weight)		
Application Method	Airless Spray	Tip range	0.48 ~ 0.59 mm
		Fan angle	55° ~ 62°
		(For T/U)	30°
	Brush	For touching up small areas only	
Mixing Ratio by Volume	BASE 3.25 / HARDENER 1		
Pot Life after Mixing	7 hours (5)	5 hours (20)	3 hours (30)
Typical Package	17L (BASE 13L, HARDENER 4L)		
	Package may vary from country to country.		
Japan Local Brand	NIPPE EPOXY PRIMER M		
Flash Point	BASE 24 , HARDENER 6		
Surface Preparation	Blast cleaned to ISO-Sa 2.5 or power tool cleaned to ISO-St 3. is recommended.		
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits. Prior to use, obtain, consult and follow the MSDS for this product concerning health and safety information.		

Marine Paint Manual

NIPPON CERAMO

Issue Date: June 2013 (ES)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) At temperatures below 5 , it will take longer to dry and harden.
- 3) If dusting may occur during application at high temperatures, use NIPPON MARINE THINNER 650.
- 4) Store the paints in paint store.