

Marine Paint Manual

Reference No. : 12 - 10

Issue Date: June 2013 (ES)

BIOFLEX 800

A tin-free, CDP (Controlled Depletion Polymer) type antifouling paint containing cuprous oxide as the main biocide, which is designed for general ocean-going ships. This product shows stable depletion rate achieved by the combination of a special hydrophobic resin and a hydrophilic resin.

Suitable Use	Antifouling for ocean-going ships		
Type	Cuprous oxide / Special synthetic polymer (Tin-free / Controlled depletion polymer type)		
Color	Red Brown, Plum, Brown		
Gloss	Semi-gloss		
Volume Solids	61 ± 2% (ISO3233:1998)		
Typical Dry Film Thickness	65 ~ 150 µm		
Approx. Wet Film Thickness	107 ~ 246 µm		
Theoretical Coverage	6.10 m ² /L (100 µm)		
Drying Time	Surface Dry	4 hours (5)	2 hours (20) 1 hour (30)
	Dry Hard	6 hours (5)	4 hours (20) 3 hours (30)
Interval before Overcoating (by self)	Min.	12 hours (5)	6 hours (20) 4 ¹ / ₂ hours (30)
	Max.	— (5)	— (20) — (30)
Interval before Immersion	Min.	24 hours (5)	12 hours (20) 12 hours (30)
Thinner	NIPPON MARINE THINNER 200 (0 ~ 5%, by weight)		
Application Method	Airless Spray	Tip range	0.69 ~ 0.84 mm
		Fan angle	62 ~ 75°
		Output pressure	above 150 kg / cm ²
Package	Brush / Roller	For touching up small areas only	
		20 L	
		Package may vary from country to country	
Flash Point	24		
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination. High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.		
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits. Prior to use, obtain, consult and follow the MSDS for this product concerning health and safety information.		

Marine Paint Manual

BIOFLEX 800

Issue Date: June 2013 (ES)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Use NIPPON MARINE THINNER 300 to wash painting appliances, hoses and guns before and after use.
- 3) The declaration letter of Tin-free Antifouling Paint would not be issued if mixed with the other antifouling paints product or another chemical products.
- 4) For application at new-building and the first application at maintenance and repair, make sure to apply the brown colour of this product as a basecoat.
- 5) After A/C touch-up on the substrates and exposed A/C parts, the brown colour of this product has to be touched up as a basecoat.
- 6) Store the paints in paint store.