

# Marine Paint Manual

Reference No. : 13 - 01  
Issue Date: April 2011 (ES)

## TETZSOL P-200 ECO

A silicone alkyd resin based primer, which is best to use for steel areas where heat resistance up to 200 is required. It does not contain hazardous heavy metal contents such as chrome or lead.

Suitable Use	Heat-resistant primer for boilers, engines, radiators, etc.		
Type	Silicone alkyd (up to 200 )		
Color	Red Oxide		
Gloss	Flat		
Volume Solids	42 ± 2 % (ISO3233:1998)		
Typical Dry Film Thickness	20 ~ 30 μm		
Approx. Wet Film Thickness	48 ~ 71 μm		
Theoretical Coverage	16.80 m <sup>2</sup> / L (25 μm)		
Drying Time	Surface Dry	30 minutes (5 )	20 minutes (20 ) 15 minutes (30 )
	Dry Hard	16 hours (5 )	4 hours (20 ) 3 hours (30 )
Interval before Overcoating ( by self )	Min.	16 hours (5 )	4 hours (20 ) 3 hours (30 )
	Max.	7 days (5 )	7 days (20 ) 7 days (30 )
Thinner	NIPPON MARINE THINNER 500 ( 0 ~ 10%, by weight )		
Application Method	Airless Spray	Tip range	0.33 mm
		Fan angle	55 ~ 69°
		Output pressure	120 ~ 150 kg / cm <sup>2</sup>
	Brush / Roller	For touching up small areas only	
Package	18kg Package may vary from country to country.		
Japan Local Brand	TETZSOL P - 500 ECO		
Flash Point	28		
Surface Preparation	Blast cleaned to ISO-Sa 2.5 or power tool cleaned to ISO-St 3.0 is recommended.		
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits. Prior to use, obtain, consult and follow the MSDS for this product concerning health and safety information.		

# Marine Paint Manual

TETZSOL P-200 ECO  
Issue Date: April 2011 (ES)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Strictly adhere to the painting intervals. Detachment may occur when the specified interval is exceeded.
- 3) Heating up to 180 for 30 minutes is essential to achieve the designated film performance.
- 4) Detachment may occur if the coating is heated and dried at a rapidly rising temperature due to machinery operation. To prevent this, slowly increase the temperature by no more than 200 per hour or run the machinery intermittently.
- 5) Store the paints in paint store.