

Marine Paint Manual

Reference No. :E 10/16
Issue Date: February 2017 (EU)

UNIPRIME 30 (E)

A high performance one-pack anticorrosive with good resistance to water, seawater and alkaline. It has tie-coat property and superior hold-up property which enables high film build. It shows excellent adhesiveness to various A/F paints and NIPPON A-MARINE FINISH.

Suitable Use	Anticorrosive for hull		
Type	Special synthetic resin (Aluminium)		
Color (Product Code)*	Silver (CRGD 9206)*	Reddish Silver (CRGD 9406)*	
		*Not color code (See note 3)	
Gloss	Flat		
Volume Solids	46 ± 2% (ISO3233:1998)		
Typical Dry Film Thickness	70 µm		
Approx. Wet Film Thickness	152 µm		
Theoretical Coverage	6.57 m ² / L (70 µm)		
Drying Time	Surface Dry	1 hour (5°C)	30 minutes (20°C) 20 minutes (30°C)
	Dry Hard	7 hours (5°C)	4 hours (20°C) 3 hours (30°C)
Interval before Overcoating (by self)	Min.	24 hours (5°C)	16 hours (20°C) 8 hours (30°C)
	Max.	— (5°C)	— (20°C) — (30°C)
Thinner (Code. No.)	NIPPON MARINE THINNER 200 (VCC 20M) / 0 ~ 5%, by volume		
Application Method	Airless Spray	Tip range	0.48 ~ 0.53 mm (0.019" - 0.021")
		Fan angle	55 ~ 69°
		Output pressure	100 ~ 150 kg / cm ²
Package	Brush	For touching up small areas only	
	20L	Package may vary from country to country.	
Japan Local Brand	UNIPRIME A/C		
Flash Point	24 °C		
Surface Preparation	Blast cleaned to ISO-Sa 2 ¹ / ₂ or power tool cleaned to St 3 is recommended.		
Generals	For commercial use only. Attention - Avoid exposure - obtain special instructions before use.		
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)		
	Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.		
	Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.		

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Store the paints in paint store.
- 3) This code is internal product code of NPMEU. Please be careful as it isn't color code.