

Marine Paint Manual

Reference No. : 15 - 01B

Issue Date: March 2019 (ES)

LF-Sea 150 HyB

A biomimetic super-low-friction antifouling that works using a patented water trapping function to lower the hydrodynamic footprint of the hull. Stable and long term antifouling is guaranteed by the using of a low friction special silyl acrylate copolymer. The combination of the clean hull, accurate and predictable low friction and the unique water-trapping technology gives a verifiable effect, lowering the ship's surface friction leading to fuel and CO₂ emission savings. It can be applied over existing antifouling.

Suitable Use	For ocean going vessels (Medium to high speed)				
Type	Special silyl acrylate copolymer (Tin-free / Super low friction / Hydrolysis / Fuel-saving / Lower CO ₂ emissions / High solid)				
Colour	B Brown, B Light Brown				
Gloss	Semi-gloss				
Volume Solids	60 ± 2% (ISO3233:1998)				
Typical Dry Film Thickness	80 ~ 150 μm				
Approx. Wet Film Thickness	133 ~ 250 μm				
Theoretical Coverage	6.00 m ² / L (100 μm)				
Drying Time	Surface Dry	1 hour (5°C)	40 minutes (20°C)	30 minutes (30°C)	
	Dry Hard	3 hours (5°C)	1 hour (20°C)	40 minutes (30°C)	
Interval before Overcoating (by self)	Min.	6 hours (5°C)	4 hours (20°C)	3 hours (30°C)	
	Max.	— (5°C)	— (20°C)	— (30°C)	
Interval before Immersion (100μm)	Min.	18 hours (5°C)	12 hours (20°C)	10 hours (30°C)	
		※ Refer to Note (4).			
Thinner	NIPPON MARINE THINNER 300 (0 ~ 5%, by volume)				
Application Method	Airless Spray	Tip range	0.59 ~ 0.69 mm		
		Fan angle	62 ~ 69°		
		Output pressure	above 150 kg / cm ²		
Typical Package	Brush / Roller	For touching up small areas only			
		20 Liter			
		Package may vary from country to country.			
Japan Local Brand	LF-Sea 150 HyB				
Flash Point	24 °C				
Surface Preparation	All surfaces to be coated should be clean, dry and free from any contamination, detachment or other defects. High pressure fresh water wash and remove all oil / grease, soluble contaminants, corrosion or any foreign materials.				

Marine Paint Manual

LF-Sea 150 HyB

Issue Date: March 2019 (ES)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Use NIPPON MARINE THINNER 300 to wash painting appliances, hoses and guns before and after use.
- 3) The declaration letter of Tin-free Antifouling Paint would not be issued if mixed with the other antifouling paints product or another chemical products.
- 4) Interval before immersion is related to ambient conditions, ventilation, film thickness, and number of coats and will be affected correspondingly. Contact us for actual application.
- 5) Store the paints in paint store.