

Marine Paint Manual

Reference No. 17 - 09

Issue Date: January 2019 (ES)

AQUATERRAS A/C LT

AQUATERRAS A/C LT is a two-pack, high volume solid epoxy anticorrosive (low temperature version) aiming for less volatile organic compounds. Providing good adhesion property to our biocide free self-polishing antifouling coating "AQUATERRAS" series, this epoxy coating offers excellent anti-abrasion property and resistant to water, seawater, and cathodic protection, it is suitable for underwater hulls, boottop, topsides, decks and holds etc. It can be overcoated with various kinds of finishes.

Suitable Use	Anticorrosive for hulls, decks and holds, etc. (Special anticorrosive for AQUATERRAS series)					
Type	Epoxy (Abrasion resistant / LT type / High build / Two-pack)					
Color	Red oxide, Gray					
Gloss	Semi-gloss					
Volume Solids	74 ± 2% (ISO3233:1998)					
Typical Dry Film Thickness	125 ~ 250 μm					
Approx. Wet Film Thickness	169 ~ 338 μm					
Theoretical Coverage	4.22 m ² /L (175 μm)					
Drying Time	Surface Dry	1 hour	(5°C)	40 minutes	(10°C)	20 minutes (20°C)
	Dry Hard	24 hours	(5°C)	16 hours	(10°C)	10 hours (20°C)
	Full Cure	10 days	(5°C)	7 days	(10°C)	5 days (20°C)
Interval before Overcoating (by self : Immersed area)	Min.	24 hours	(5°C)	16 hours	(10°C)	10 hours (20°C)
	Max.	30 days	(5°C)	30 days	(10°C)	14 days (20°C)
Interval before Overcoating (by self : Exposed area)	Min.	24 hours	(5°C)	16 hours	(10°C)	10 hours (20°C)
	Max.	—	(5°C)	—	(10°C)	— (20°C)
Thinner	NIPPON MARINE THINNER 600 (0 ~ 10%, by volume)					
Application Method	Airless Spray	Tip range	0.48 ~ 0.59 mm			
		Fan angle	55° ~ 62°			
		(For T/U)	30°			
		Output pressure	150 ~ 200 kg/cm ²			
	Brush / Roller	For touching up small areas only				
Mixing Ratio by Volume	BASE 4.93 / HARDENER 1					
Pot Life after Mixing	4 hours (5°C) 3 hours (10°C) 2 hours (20°C)					
Typical Package	20 L (BASE 16.6L, HARDENER 3.4 L)					
	Package may vary from country to country.					
Japan Local Brand	AQUATERRAS A/C LT					
Flash Point	BASE 29°C, HARDENER 25°C (ISO3679:2015)					
Surface Preparation	Blast cleaned to ISO-Sa 2 ¹ / ₂ or power tool cleaned to St 3 is recommended.					

Marine Paint Manual

AQUATERRAS A/C LT

Issue Date: January 2019 (ES)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)

Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.

Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Store the paints in paint store.